

# Hydro-Solv™ 9250

## Hydronic System Cleaner For Aluminum & Multi-Metal Boilers

- Cleans solder flux, cutting oil, rust and dirt from new systems
- Concentrated for large volume systems
- Removes scale and corrosion
- Recover lost operating efficiency
- Lower heating bills
- Dilutes One-gallon/250 gallons
- Effectively cleans aluminum, iron, copper, brass and stainless

### SPECIALLY FORMULATED FOR HYDRONIC SYSTEMS

- Safe on all Hydronic System Components when used as directed
- Non-Hazardous
- Environmentally friendly
- Contains NO acids or heavy metals

**“BE PROFESSIONAL—PROPERLY CLEAN THE SYSTEM”**

*Let Hydro-Solv™9250 be part of your Hydronic Maintenance Program*



**Rhomar**  
Water Management, Inc.

Springfield, Missouri 65801 • 417.862.2600 • 800.543.5975

# Hydro-Solv™ 9250 Product Data Sheet

## Hydronic System Cleaner for Aluminum and Multi-Metal Boilers

### ADVANTAGES:

**Hydro-Solv™ 9250** is the product of choice for “online” and new installation clean-up jobs. It is recommended that all new hydronic systems be cleaned and passivated with **Hydro-Solv™ 9250** prior to putting the system in service. It will penetrate and disperse a broad range of mineral and organic foulants and help recover lost efficiency in older fouled and corroded systems. In addition, **Hydro-Solv™ 9250** contains a corrosion inhibitor additive that will help protect system metals during the cleaning process. When used as directed, it effectively cleans iron, copper, aluminum, brass, and stainless steel. **Hydro Solv™ 9250** will not harm flexible tubing and contains no acids or heavy metals.

### DIRECTIONS:

1. Open all zone valves on system to be cleaned.
  2. Thoroughly flush the system to remove as many contaminants as possible and the water appears clean.
  3. Add **Hydro-Solv™ 9250** cleaner at the rate of 1 gallon per 250 gallons of system water or until a red color is visible. When used as directed, **Hydro-Solv™ 9250** is safe to run through the boiler during the cleaning process.
  4. **New Installations:** Circulate **Hydro-Solv™ 9250** cleaner 4-6 hours, then flush the system until the flush water becomes clear. Continue to flush the system until the pH is the same as makeup water.  
**Older Systems: For non-aluminum cleaning:** circulate for several days or until water becomes visibly fouled, then flush until clear. Older systems with black iron pipe may require additional cleaning to remove all the debris. Repeat the cleaning process until water remains clear. Thoroughly flush to remove cleaner - pH should be the same as the makeup water.  
**Aluminum Boilers:** Cleaning time should be limited to 8 hours when circulating through an aluminum boiler. This restriction can be avoided by bypassing the boiler. Many existing systems will contain glycol or additives that are not compatible with aluminum and produce a pH that may be too high. After cleaning, be sure to flush the system with makeup water until the fluid pH is 8.0 or below. This will help to ensure that all of the old fluid and cleaning solution are removed. (Note: the low pH range will be limited to makeup water pH.)
- NOTE:** Heating the system to operating temperature will improve results.
5. After cleaning and flushing, add **Pro-Tek®** corrosion inhibitor treatment or **RhoGard™** inhibited glycol for long-term protection.

DISTRIBUTED BY: